Proc. Estonian Acad. Sci. Chem., 2005, **54**, 2, 85–93 https://doi.org/10.3176/chem.2005.2.04

# Comparative semiempirical, ab initio, and DFT study of interactions between polypyrrole pentamer dication and some anions

Peeter Burk<sup>a\*</sup>, Imbi Rauk<sup>b</sup>, and Tarmo Tamm<sup>c</sup>

<sup>a</sup> Institute of Chemical Physics, University of Tartu, Jakobi 2, 51014 Tartu, Estonia

<sup>b</sup> Institute of Physical Chemistry, University of Tartu, Jakobi 2, 51014 Tartu, Estonia

<sup>c</sup> Institute of Molecular and Cell Biology, University of Tartu, Riia 23, 51010 Tartu, Estonia

Received 9 February 2005, in revised form 21 April 2005

**Abstract.** Complexes between pyrrole pentameter dication and chloride, bromide, and perchlorate anions were studied using AM1, PM3,  $HF/3-21+G^{(*)}$ , and  $B3LYP/6-31+G^{**}$  methods. The resulting complexation energies were in agreement with the trends in the ionic radiuses of the anions. Semiempirical methods were found to underestimate the complexation energy of the perchlorate anion and in the case of PM3 also the bromide anion.  $HF/3-21+G^{(*)}$  also gave a too narrow range of complexation energies, in addition nonplanarity of the dication was not observed. The DFT B3LYP/6-31+G<sup>\*\*</sup> method, while being most consistent, yielded some complexation energies with slightly higher BSSE than expected.

Key words: polypyrrole, anions, DFT, ab initio, AM1, PM3.

### **INTRODUCTION**

Intrinsic conducting polymers with conjugated double bonds have been under intense investigation for more than twenty years already. Polypyrrole (PPy), together with polythiophene and polyaniline, is among the most promising candidates for wide applications for its good environmental stability, simple synthesis, and high conductivity. The applications of PPy include (but are not limited to) various sensors, functional membranes, selective coatings, polymeric batteries and capacitors, electrochromic windows and displays, etc. [1, 2].

Polypyrrole is commonly synthesized by means of the electrochemical polymerization of pyrrole from a solution of some supporting electrolyte. Both aqueous

<sup>&</sup>lt;sup>\*</sup> Corresponding author, burk@ut.ee

and nonaqueous solutions can be used. The thickness, structure, and other properties of the polymer film formed on the anode can be varied within a wide range by altering the electrodeposition conditions or the composition of the solution. The role of the anions incorporated into the polymer film in order to maintain electroneutrality is not limited to the stabilization of the opposite charge. The anions also play a key role in the formation of the structure of the polymer chains, participating therefore in the origination of the properties of the whole polymer film [1, 3–5]. Thorough understanding of the influence of anions on the structure and properties of the conducting polymers would, therefore, enable the synthesis of conducting polymers of specific predefined properties. While a wide variety of experimental methods have been applied for the investigation of the influence of dopant anions on the properties of conducting polymers [6-10], theoretical treatments are commonly limited to substituted or unsubstituted neutral oligomers [11, 12] or their cationic and anionic forms [13, 14]. Lattice simulations of the placement and movement of chloride and tetrafluoroborate anions inside polymer films [15, 16] are among the very few investigations reported.

#### METHODOLOGY

All oligopyrroles dications and their complexes with anions were treated as conventional closed shell systems. No solvation models were applied, as the use of continuum models can hardly be justified for polymer films containing only limited solvent molecules per chain and in the vicinity of charged electrodes. Small hard inorganic anions are known to have strong interaction with conducting polymers, and the amount of solvent inside the polymer as well as solvent movement into and out of the polymer during redox cycling is relatively limited [7–10]. There is very little experimental evidence about the actual structure, composition, and interactions inside PPy films. While most investigations presume that PPy chains always take the planar all-anti form, a series of STM images of PPy doped with large (polymeric) anions published already a while ago [17–19] suggest that under some conditions the helical structures, apparently formed from all-syn pyrrole chains, are the predominant form of the polymer. It has also been shown that the rotational barriers between pyrrole units are not very high [11, 20], therefore, only the energetically more favoured all-syn oligomers [21] were considered in the present study for anion-charged oligomer complexes. While the simple model used in this work cannot accurately reflect the reality in its full complexity, it is focused on the anion-polymer chain interactions. The choice of short oligomers enables the search for fully relaxed conformations with no periodic or planarity constraints using reasonably elaborate methods.

Semiempirical calculations with AM1 [22] and PM3 [23] methods were carried out using the Spartan program [24]. Standard ab initio (HF) calculations using the  $3-21+G^{(*)}$  [25–29] basis set (for bromine polarization functions from standard 6-31+G\* basis set were added to 3-21+G basis) and density functional calculations with the B3LYP hybrid functional [30–33] and 6-31+G\*\* [29,

34-37] basis set were performed using the Gaussian 03 [38] program package. All geometries were fully optimized and the frequencies were calculated at the respective levels. Harmonic frequency analysis indicated that all structures were minima on the potential energy surface (i.e. number of imaginary frequencies, NImag = 0). No scaling was applied to the obtained frequencies for the calculation of enthalpies and free energies. Heats of formation calculated with AM1 and PM3 methods are reported in Table 1. Total energies, enthalpies, and Gibbs free energies calculated with ab initio and DFT methods are given in Table 2.

Complexation energies were calculated in the usual way, that is as energies for reaction (1)

$$Py_5^{2+} + An^{-} = [Py_5An]^{+},$$
(1)

$$E(1) = E([Py_5An]^+) - [(E(Py_5^{2+}) + E(An^-)],$$
(2)

where E denotes either electronic energy, enthalpy, or free energy. It is well known that complexation energies calculated in such a way may be seriously

Table 1. Heats of formation ( $\Delta H_f$ , in kcal/mol) calculated with AM1 and PM3 methods

	$\Delta H_{f}(AM1)$	$\Delta H_{f}(PM3)$
Cl	-37.7	-51.2
Br <sup>-</sup>	-20.4	-56.2
$ClO_4^-$	166.5	-128.1
PPy <sup>2+</sup>	576.9	517.3
$PPy^{2+}-Cl^{-}$	352.8	277.4
PPy <sup>2+</sup> –Br <sup>–</sup>	372.4	291.6
PPy <sup>2+</sup> –ClO <sub>4</sub> <sup>-</sup>	587.2	238.9

**Table 2.** Electronic energies (E), enthalpies (H), and free energies (G) calculated at the HF/3- $21+G^{(*)}$  and B3LYP/6-31+G\*\* levels (in a.u.)

	Е	Н	G			
HF/3-21+G <sup>(*)</sup>						
Cl⁻	-457.46831	-457.46595	-457.48333			
Br <sup>-</sup>	-2560.31135	-2560.30899	-2560.32753			
$ClO_4^-$	-754.96998	-754.94954	-754.97947			
PPy <sup>2+</sup>	-1033.28705	-1032.89704	-1032.96274			
$PPy^{2+}-Cl^{-}$	-1491.05121	-1490.65894	-1490.72663			
PPy <sup>2+</sup> –Br <sup>–</sup>	-3593.88676	-3593.49456	-3593.56351			
PPy <sup>2+</sup> -ClO <sub>4</sub> <sup>-</sup>	-1788.53563	-1788.12267	-1788.19883			
B3LYP/6-31+G**						
Cl <sup>-</sup>	-460.27473	-460.27237	-460.28975			
Br <sup>-</sup>	-2571.80318	-2571.80082	-2571.81936			
$ClO_4^-$	-760.83085	-760.81150	-760.84426			
PPy <sup>2+</sup>	-1045.64298	-1045.28489	-1045.35772			
$PPy^{2+}-Cl^{-}$	-1506.21870	-1505.85770	-1505.93243			
PPy <sup>2+</sup> –Br <sup>–</sup>	-3617.75114	-3617.39035	-3617.46545			
PPy <sup>2+</sup> –ClO <sub>4</sub> <sup>-</sup>	-1806.74592	-1806.36526	-1806.44749			

Table 3. Calculated complexation energies ( $\Delta E$ ), enthalpies ( $\Delta H$ ), and free energies ( $\Delta G$ ), all in kcal/mol

	AM1	PM3	HF		B3LYP			
	$\Delta H$	$\Delta H$	$\Delta E$	$\Delta H$	$\Delta G$	$\Delta E$	$\Delta H$	$\Delta G$
PPy <sup>2+</sup> -Cl <sup>-</sup>	-186.4	-188.7	-179.8	-179.9	-170.2	-188.3	-187.9	-178.2
PPy <sup>2+</sup> –Br <sup>–</sup>	-184.1	-169.5	-172.4	-172.5	-162.9	-181.3	-181.1	-170.9
$PPy^{2+}-ClO_4^{-}$	-156.2	-150.3	-160.7	-159.1	-146.9	-167.8	-165.8	-151.1

affected by the artificial lowering of the energy of the complex due to the basis set superposition error (BSSE) (see e.g. [39], p. 172). We estimated the magnitude of the BSSE using the standard counterpoise correction method [40–41]. The size of BSSE is thought to diminish with the increase of basis set. However, in the case of the PPy–Br complex the BSSE is found to be greater at the B3LYP/6-31+G<sup>\*\*</sup> level than at the HF/3-21+G<sup>(\*)</sup> level, in accordance with our earlier claim that the 6-31+G<sup>\*</sup> basis set for bromine is not well balanced [42]. Calculated complexation energies, enthalpies, and free energies are given in Table 3 with BSSE correction included.

### **RESULTS AND DISCUSSION**

### Energies

Ab initio and DFT complexation energies, given in Table 3, agree reasonably well with each other. The trend in complexation energies calculated at that level follows reasonably well the ionic radiuses (1.67, 1.92, and 2.40 Å for chloride, bromide, and perchlorate, respectively [43]) of the studied ions (Fig. 1), indicating that the interaction between cations and the pyrrole pentamer dication is mainly ionic. The semiempirical AM1 and PM3 methods give the same complexation energy order as ab initio and DFT calculations, while the differences between complexation energies of different anions do not follow those calculated at higher levels so closely. It seems that both semiempirical methods underestimate the complexation energies for the perchlorate anion (probably due to the lack of d-functions and consequent rigidity of the basis set).

The difficulties with semiempirical methods became especially clear when comparing relative complexation energies (see Table 4). It is apparent that both the ab initio and DFT methods used give these in good accordance, while the results of AM1 and PM3 methods differ considerably among themselves and also from the results of the ab initio and DFT calculations. The discrepancies among the semiempirical results are largest for the case of bromide anions, where the PM3 parametrization largely underestimates the complexation energies of the bromide anion. Compared to the semiempirical and DFT methods, the HF/3-21+G<sup>(\*)</sup> method somewhat underestimates the differences in complexation energies between the oligomer dication and different anions.



**Fig. 1.** Dependence of the complexation energies (kcal/mol) calculated at HF/3-21+ $G^{(*)}$  ( $\Box$ ) and B3LYP/6-31+ $G^{**}$  ( $\bigcirc$ ) levels from ionic radiuses (Å, [43]).

**Table 4.** Relative complexation enthalpies ( $\Delta\Delta H$ , relative to PPy<sup>2+</sup>–Cl<sup>-</sup>, in kcal/mol)

	AM1	PM3	HF	B3LYP
PPy <sup>2+</sup> -Br <sup>-</sup>	-2.3	-19.2	-7.4	-6.8
PPy <sup>2+</sup> -ClO <sub>4</sub> <sup>-</sup>	-30.2	-38.4	-20.8	-22.1

### Geometries

The geometries of PPy pentamer and its complexes are given in Fig. 2. The most striking feature of structures in Fig. 2 is the nonplanarity of the N–H bonds of pyrroles with the rest of pyrrole ring in free pentamer dication, observed at the B3LYP/6-31+G\*\* level. The nonplanarity is greatest at the central pyrrole unit and diminishes towards the ends of the PPy chain. The pyrrole units in the PPy pentamer dication were found to be twisted with respect to each other at the B3LYP/6-31+G\*\* level. Similar nonplanarity of the N–H bond in pyrrole fragments, but only for the central fragment, was observed also at the AM1 and PM3 levels of calculations. The HF/3-21+G<sup>(\*)</sup> calculations yielded a perfectly planar pentamer.

Upon complexation with an anion the PPy pentamer dication becomes planar to allow better interaction with the anion. The only exception here is the complex of the PPy pentamer dication with the perchlorate anion, where the N–H bond of the central pyrrole unit is again out of the plane defined by the rest of the PPy pentamer dication.



**Fig. 2.** Structure of pentapyrrole dication (a) and its complexes with chloride (b), bromide (c), and perchlorate (d) anions calculated at the B3LYP/6-31+G\*\* level.

(c)

(d)

### CONCLUSIONS

The complexes of pyrrole oligomer dications with three inorganic anions were studied using semiempirical, HF, and DFT methods. The resulting complexation energies are in agreement with the ionic radiuses of the anions. The geometries of the dication and of the complex with the perchlorate anion were found to be nonplanar according to DFT calculations. Such calculations of relatively non-trivial systems should always be done using several computational methods as the results of different methods are seldom matching. In the present case, semi-empirical methods underestimated the complexation energy of the perchlorate anion and in the case of PM3 also the bromide anion. HF/3-21+G<sup>(\*)</sup> has a limited range of complexation energies, making them look more similar; besides, non-planarity of the dication is not observed. The DFT B3LYP/6-31+G\*\* method, while being most consistent, yields some complexation energies with a slightly higher BSSE than expected.

### REFERENCES

- 1. Skotheim, T. A., Elsenbaumer, R. & Reynolds, J. (eds.) *Handbook of Conducting Polymers*. Second edition. Marcel Dekker, New York, Vols. 1 and 2, 1998.
- Wang, L.-X., Li, X.-G. & Yang, Y.-L. Preparation, properties and applications of polypyrroles. Reactive and functional polymers. *React. Funct. Polym.*, 2001, 47, 125–139.

- Tamm, J., Alumaa, A., Hallik, A., Silk, T. & Sammelselg, V. Nature of ion sensitivity of polypyrrole electrodes. *J. Electroanal. Chem.*, 1996, 414, 149–158.
- Lee, H., Yang, H. & Kwak, J. Dependence of the electrochemical behavior of poly(N-phenylpyrrole) films on the type of anion and solvent used in the electropolymerization. *J. Phys. Chem. B.*, 1999, **103**, 6030–6035.
- Tamm, J., Alumaa, A., Hallik, A., Johanson, U., Tamm, L. & Tamm, T. Influence of anions on electrochemical properties of polypyrrole-modified electrodes. *Russian J. Electrochem.*, 2002, 38, 210–216.
- Briseno, A. L., Baca, A., Zhou, Q., Lai, R. & Zhou, F. Quantification of dopant ions in polypyrrole films with electrochemical ICP-atomic emission spectrometry and comparison to electrochemical quartz crystal microbalance studies. *Anal. Chim. Acta*, 2001, 441, 123–134.
- Vorotyntsev, M. A., Vieil, E. & Heinze, J. Ionic exchange of the polypyrrole film with the PC lithiumperchlorate solution during the charging process. *Electrochim. Acta*, 1996, **41**, 1913–1920.
- Vorotyntsev, M. A., Vieil, E. & Heinze, J. Charging process in polypyrrole films: effect of ion association. J. Electroanal. Chem., 1998, 450, 121–141.
- Wilson, R. W., Cubitt, R., Glidle, A., Hillman, A. R., Saville, P. M. & Vos, J. G. A neutron reflectivity study of [Os(bipy)<sub>2</sub>(PVP)<sub>10</sub>Cl]<sup>+</sup> polymer film modified electrodes: effect of redox state and counter ion. *Electrochim. Acta*, 1999, 44, 3533–3548.
- Jureviciute, I., Bruckenstein, S. & Hillman, A. R. Counterion specific effects on charge and solvent trapping in poly(vinylferrocene). J. Electroanal. Chem., 2000, 488, 73–81.
- Millefiori, S. & Alparone, A. Theoretical study of the structure and torsional potential of pyrrole oligomers. J. Chem. Soc., Faraday Trans., 1998, 94, 25–32.
- DiCésare, N., Belletête, M., Leclerc, M. & Durocher, G. HF/3-21G\* ab initio calculations on methoxy-substituted bithiophenes. J. Mol. Struct. (Theochem), 1999, 467, 259–273.
- Hernández, V., Ramírez, F. J., Casado, J., Enríquez, F., Quirante, J. J. & López Navarrete, J. Y. Ab initio RHF/6-31G\*\* theoretical study of thiophene derivatives: 2-methylthiophene and 3-methylthiophene. J. Mol. Struct. (Theochem), 1997, 410–411, 311–314.
- 14. Yurtsever, E. A quantum mechanical study of the electrochemical polymerization of pyrrole. *Synth. Met.*, 2001, **119**, 227–228.
- Veluri, K., Corish, J., Morton-Blake, D. A. & Bénière, F. A lattice simulation investigation of the migration of chloride ions in doped polypyrrole and polythiophene. J. Mol. Struct. (Theochem), 1995, 334, 109–120.
- Veluri, K., Corish, J., Morton-Blake, D. A. & Bénière, F. A lattice simulation of the migration of the BF<sub>4</sub><sup>-</sup> ion in polythiophene and polypyrrole lattices. *J. Mol. Struct. (Theochem)*, 1996, 365, 13–19.
- Yang, R., Dalsin, K. M., Evans, D. F., Christensen, L. & Hendrickson, W. A. STM imaging of electropolymerized, doped polypyrrole. Visual evidence of semicrystalline and helical nascent polymer growth. J. Phys. Chem., 1989, 93, 511–512.
- Yang, R., Evans, D. F., Christensen, L. & Hendrickson, W. A. Scanning tunneling microscopy evidence of semicrystalline and helical conducting polymer structures. *J. Phys. Chem.*, 1990, 94, 6117–6122.
- Yang, R., Naoi, K., Evans, D. F., Smyrl, W. H. & Hendrickson, W. A. STM study of electropolymerized polypyrrole with polymeric anion. *Langmuir*, 1991, 7, 556–558.
- Padalla-Campos, L. & Toro-Labbé, A. A model potential for the internal rotation of neighbouring rings of bithiophene and bipyrrole. J. Mol. Struct. (Theochem), 1995, 330, 223–229.
- Tamm, T., Tamm, J. & Karelson, M. Theoretical study of the effect of counterions on the structure of pyrrole oligomers. *Int. J. Quant. Chem.*, 2002, 88, 296–301.
- 22. Dewar, M. J. S., Zoebisch, E. G., Healy, E. F. & Stewart, J. J. P. AM1: a new general purpose quantum mechanical molecular model. *J. Am. Chem. Soc.*, 1985, **107**, 3902–3909.
- 23. Stewart, J. J. P. Optimization of parameters for semiempirical methods. I. Method. J. Comput. Chem., 1989, **10**, 209–220.
- 24. Spartan'02, Wavefuction Inc., 18401 Von Karman Avenue, Suite 370, Irvine, Ca 92612 (http://www.wavefun.com).

- 25. Binkley, J. S., Pople, J. A. & Hehre, W. J. Self-consistent molecular orbital methods. 21. Small split-valence basis sets for first-row elements. *J. Am. Chem. Soc.*, 1980, **102**, 939–947.
- 26. Gordon, M. S., Binkley, J. S., Pople, J. A., Pietro, W. J. & Hehre, W. J. Self-consistent molecular-orbital methods. 22. Small split-valence basis sets for second-row elements. J. Am. Chem. Soc., 1983, 104, 2797–2803.
- Dobbs, K. D. & Hehre, W. J. Molecular orbital theory of the properties of incorganic and organometallic compounds 4. Extended basis sets for third- and fourth-row, main-group elements. J. Comput. Chem., 1986, 7, 359–378.
- 28. Pietro, W. J., Francl, M. M., Hehre, W. J., DeFrees, D. J., Pople, J. A. & Binkley, J. S. Selfconsistent molecular orbital methods. XXIV. Supplemented small split-valence basis sets for second-row elements. J. Am. Chem. Soc., 1982, **104**, 5039–5048.
- Clark, T., Chandrasekhar, J. & Schleyer, P. V. R. Efficient diffuse function-augmented basissets for anion calculations. 3. The 3-21+G basis set for 1st-row elements, LI-F. J. Comp. Chem., 1983, 4(3), 294–301.
- Becke, A. D. Density-functional thermochemistry. 3. The role of exact exchange. J. Chem. Phys., 1993, 98, 5648–5652.
- Lee, C., Yang, W. & Parr, R. G. Development of the Colle-Salvetti correlation-energy formula into a functional of the electron density. *Phys. Rev. B*, 1988, 37, 785–789.
- Vosko, S. H., Wilk, L. & Nusair, M. Accurate spin-dependent electron liquid correlation energies for local spin density calculations: a critical analysis. *Can. J. Phys.*, 1980, 58, 1200–1211.
- Stephens, P. J., Devlin, F. J., Chabalowski, C. F. & Frisch, M. J. Ab initio calculation of vibrational absorption and circular dichroism spectra using density functional force fields. *J. Phys. Chem.*, 1994, **98**, 11623–11627.
- Hehre, W. J., Ditchfield, R. & Pople, J. A. Self-consistent molecular-orbital methods. XII. Further extension of Gaussian-type basis sets for use in molecular orbital studies of organic molecules. J. Chem. Phys., 1972, 56, 2257–2261.
- 35. Dill, J. D. & Pople, J. A. Self-consistent molecular orbital methods. XV. Extended Gaussiantype basis sets for lithium, beryllium, and boron. *J. Chem. Phys.*, 1975, **62**, 2921–2923.
- 36. Franci, M. M., Petro, W. J., Hehre, W. J., Binkley, J. S., Gordon, M. S., DeFrees, D. J. & Pople, J. A. Self-consistent molecular orbital methods. XXIII. A polarization-type basis set for second-row elements. J. Chem. Phys., 1982, 77, 3654–3665.
- 37. Rassolov, V., Pople, J. A., Ratner, M. & Windus, T. L. 6-31G\* basis set for atoms K through Zn. J. Chem. Phys., 1998, 109, 1223–1229.
- 38. Frisch, M. J., Trucks, G. W., Schlegel, H. B., Scuseria, G. E., Robb, M. A., Cheeseman, J. R., Montgomery, J. A., Jr., Vreven, T., Kudin, K. N., Burant, J. C., Millam, J. M., Iyengar, S. S., Tomasi, J., Barone, V., Mennucci, B., Cossi, M., Scalmani, G., Rega, N., Petersson, G. A., Nakatsuji, H., Hada, M., Ehara, M., Toyota, K., Fukuda, R., Hasegawa, J., Ishida, M., Nakajima, T., Honda, Y., Kitao, O., Nakai, H., Klene, M., Li, X., Knox, J. E., Hratchian, H. P., Cross, J. B., Bakken, V., Adamo, C., Jaramillo, J., Gomperts, R., Stratmann, R. E., Yazyev, O., Austin, A. J., Cammi, R., Pomelli, C., Ochterski, J. W., Ayala, P. Y., Morokuma, K., Voth, G. A., Salvador, P., Dannenberg, J. J., Zakrzewski, V. G., Dapprich, S., Daniels, A. D., Strain, M. C., Farkas, O., Malick, D. K., Rabuck, A. D., Raghavachari, K., Foresman, J. B., Ortiz, J. V., Cui, Q., Baboul, A. G., Clifford, S., Cioslowski, J., Stefanov, B. B., Liu, G., Liashenko, A., Piskorz, P., Komaromi, I., Martin, R. L., Fox, D. J., Keith, T., Al-Laham, M. A., Peng, C. Y., Nanayakkara, A., Challacombe, M., Gill, P. M. W., Johnson, B., Chen, W., Wong, M. W., Gonzalez, C. & Pople, J. A. *Gaussian 03, Revision C.02*. Gaussian, Inc., Wallingford CT, 2004.
- 39. Jensen, F. Introduction to Computational Chemistry. Wiley, London, 1999.
- Boys, S. F. & Bernardi, F. The calculation of small molecular interactions by the differences of separate total energies. Some procedures with reduced errors. *Mol. Phys.*, 1970, **19**, 553– 556.
- 41. van Duijnveldt, F. B., van Duijnveldt-van de Rijdt, J. G. C. M. & van Lenthe, J. H. State of the art in counterpoise theory. *Chem. Rev.*, 1994, **94**, 1873–1875.

42. Tammiku-Taul, J., Burk, P. & Tuulmets, A. Theoretical study of magnesium compounds: the Schlenk equilibrium in gas phase and in the presence of Et2O and THF molecules. *J. Phys. Chem. A*, 2004, **108**(1), 133–139.

43. Marcus, Y. Ion Properties. Marcel-Decker, New York, 1997.

## Polüpürrooli pentameeri dikatiooni ja mõningate anioonide vaheliste interaktsioonide võrdlev poolempiiriline, *ab initio* ja DFT-uurimus

### Peeter Burk, Imbi Rauk ja Tarmo Tamm

Polüpürrooli pentameeri dikatiooni ning kloriid-, bromiid- ja perkloraatanioonide vahelisi interaktsioone on uuritud AM1-, PM3-, HF/3-21+G<sup>(\*)</sup>- ja B3LYP/6-31+G\*\*-meetoditega. Saadud komplekseerumisenergiad olid heas kooskõlas anioonide raadiuste kasvuga reas Cl<sup>-</sup>, Br<sup>-</sup>, ClO<sub>4</sub><sup>-</sup>. Poolempiirilised AM1- ja PM3meetodid alahindasid perkloraataniooni komplekseerumisenergiat, samuti alahindas PM3-meetod ka bromiidaniooni komplekseerumisenergiat. Ka HF/3-21+G<sup>(\*)</sup>-meetodi korral olid leitud komplekseerumisenergiad suhteliselt kitsas vahemikus. Kasutatud meetoditest andis parimaid tulemusi B3LYP/6-31+G\*\*, samas olid selle meetodi korral baasi superpositsiooni vead oodatust suuremad.